



Shade Fabric Report

AS4174:2018 Analysed for: Daydream Leisure Furniture

ARPANSA Reference: UVR 25-0069-3 Analysis Date: 11 Mar 2025

Sample Information

Sample Weight (gsm): 178 Instrumentation: Bentham DTMc300F s/n 14294

Specimens Tested: 10

Description: Burnt Orange #101 Sunproof Valtos Woven Shade Fabric, Umbrella Fabric - Solution Dyed Olefin

Shade Fabric Results


Cover Factor:	99.0
Shade Factor:	91.7
UV-Visible Transmittance (%):	8.3
UVR Transmittance (%):	0.3
UVR Block (%):	99.7
PAR Transmittance (%):	7.8
Designation:	Ultra-heavy cover
Colour Code:	Beige

Human Protection Results Std Dev 99.0 0.0 Ultraviolet Effectiveness (UVE%):

Most Effective **Protection Category:**

Average Transmitance vs. Wavelength (nano

UV-Visible Transmittance



Review of Results

When shade fabric is used for purposes such as shade structures for human protection, the ultraviolet effectiveness (UVE) may not be an accurate guide to the protection provided and may be less than the measured value due to variations in design, height and size of shade structures, stretching of the fabric, the distance of the fabric from the persons, the direction of sunlight, and the physical location of the persons within the shade structure (e.g. at the edge or at the centre).

Please refer to AS 4174:2018 for labelling requirements; these requirements are summarised in the email accompanying this report.

Disclaimer Material Sample

Unless otherwise stated the sample was tested unstretched, dry and in new condition. This report has been prepared in accordance with standard AS 4174:2018 - Knitted and woven shade fabrics, Appendices A, B & D. The results in this report are applicable to the sample tested and may not apply to other batches of the same material or similar materials. It is a condition of the provision of these test results that you do not use the name of the Australian Radiation Protection and Nuclear Safety Agency (ARPANSA) or the Commonwealth of Australia, or any words, marks or devices which may imply a connection with ARPANSA or the Commonwealth of Australia, in connection with the promotion or sale of your products, unless the ARPANSA has given express written authority to do so.





11 Mar 2025

Lydiawati Tjong

12 Mar 2025

Anindita Das - Technician

Lydia Tjong - Approved Signatory

ARPANSA-FORM-1883



NATA Accredited Laboratory Number: 14442 Accredited for compliance with ISO/IEC 17025 - Testing

Corporate Site Number: 22022

619 Lower Plenty Road, Yallambie, Victoria 3085 Phone: +61 3 9433 2309 E-mail: uvr-services@arpansa.gov.au Web: www.arpansa.gov.au

Page 1 of 1

This test report may only be reproduced in full and without alteration.