



Shade Fabric Report

Analysed for: Daydream Leisure Furniture

AS4174:2018

ARPANSA Reference: UVR_26-0097-4

Analysis Date: 5 Mar 2026

Sample Information

Sample Weight (gsm): 223.6 **Instrumentation:** Bentham DTMc300F s/n 14294
Specimens Tested: 10
Description: Aqua Stripe #210 Woven Shade Fabric, Sunproof Koblenz Umbrella Fabric Solution Dyed


Shade Fabric Results

Cover Factor: 99.0
Shade Factor: 97.5
UV-Visible Transmittance (%): 2.5
UVR Transmittance (%): 0.1
UVR Block (%): 99.9
PAR Transmittance (%): 3.0
Designation: Ultra-heavy cover
Colour Code: Beige

Human Protection Results

		Std Dev
Ultraviolet Effectiveness (UVE%):	99.0	0.0
Protection Category:	Most Effective	

UV-Visible Transmittance



Review of Results


When shade fabric is used for purposes such as shade structures for human protection, the ultraviolet effectiveness (UVE) may not be an accurate guide to the protection provided and may be less than the measured value due to variations in design, height and size of shade structures, stretching of the fabric, the distance of the fabric from the persons, the direction of sunlight, and the physical location of the persons within the shade structure (e.g. at the edge or at the centre).

Please refer to AS 4174:2018 for labelling requirements; these requirements are summarised in the email accompanying this report.

Disclaimer

Unless otherwise stated the sample was tested unstretched, dry and in new condition. This report has been prepared in accordance with standard AS 4174:2018 - Knitted and woven shade fabrics, Appendices A, B & D. The results in this report are applicable to the sample tested and may not apply to other batches of the same material or similar materials. It is a condition of the provision of these test results that you do not use the name of the Australian Radiation Protection and Nuclear Safety Agency (ARPANSA) or the Commonwealth of Australia, or any words, marks or devices which may imply a connection with ARPANSA or the Commonwealth of Australia, in connection with the promotion or sale of your products, unless the ARPANSA has given express written authority to do so.

Material Sample



5 Mar 2026

Asanka Jayawardena - Technician

5 Mar 2026

Lydia Tjong - Approved Signatory


ARPANSA-FORM-1883

Page 1 of 1



NATA Accredited Laboratory Number: 14442
Accredited for compliance with ISO/IEC 17025 - Testing
Corporate Site Number: 22022

619 Lower Plenty Road, Yallambie, Victoria 3085
Phone: +61 3 9433 2309
E-mail: uvr-services@arpansa.gov.au
Web: www.arpansa.gov.au



This test report may only be reproduced in full and without alteration.